



C35E
Non-alloy special steel

(W. NR. 1.1181)

CHEMICAL COMPOSITION: (heat analysis according to the EN ISO 683-1:2018 standard)

	C %	Si %	Mn %	P %	S %	Cr %	Ni %	Mo %	Cu%	Cr+Mo+Ni %
FROM	0,32	0,10	0,50	-	-	-	-	-	-	-
TO	0,39	0,40	0,80	0,025	0,035	0,40	0,40	0,10	0,30	0,63

*** MECHANICAL FEATURES:** (according to the EN 10277:2018 standard)

Thickness mm	Rolled + peeled rolled (+SH)		Cold drawn (+C)		
	hardness HB	Rm (MPa)	Rp _{0,2} minimum values (MPa)	Rm (MPa)	A ₅ % minimum values
≥5≤10			510	650 - 1000	6
>10≤16			420	600 - 950	7
>16≤40	156 - 204	520 - 700	320	580 - 880	8
>40≤63	156 - 204	520 - 700	300	550 - 840	9
>63≤100	156 - 204	520 - 700	270	520 - 800	9

* Delivery condition: as rolled.

PROPERTIES :

Weldability:

It can be welded quite well without any precautions.

Hardenability:

Low hardenability; core quenching in water till a diameter of 12-15 mm; as far as bigger diameters are concerned, it hardens only till a certain depth, inversely proportional to diameter, like all non-alloy steels with medium-high carbon content.

Notes :

CORRESPONDENCE WITH OTHER STANDARDS (purely as an indication) :

UNI 7845 C35	DIN 17200 CK35	AISI-SAE 1035	AFNOR 35-552 XC38H1
------------------------	--------------------------	-------------------------	-------------------------------