



E360
Non-alloy steel for structural purposes

(W. NR. 1.0070)

CHEMICAL COMPOSITION: (heat analysis according to the EN 10025-2:2019 standard)

	C %	Si %	Mn %	P %	S %	N %	Cu %
FROM	-	-	-	-	-	-	-
TO	-	-	-	0,045	0,045	0,012	-

***MECHANICAL FEATURES:** there aren't any indications for the drawn products +C

* Delivery condition: as rolled.

PROPERTIES:

Weldability:

Failing any prescriptions concerning chemical composition, no technical data about this steel weldability are available.

Notes:

CORRESPONDENCE WITH OTHER STANDARDS (purely as an indication) :

EN 10025-2:2019 E360	EN 10025:90 Fe 690-2	UNI 7070 Fe 690	DIN 17 100 St 70-2	NF A35-501 A 70-2
--------------------------------	--------------------------------	---------------------------	------------------------------	-----------------------------